

PRODUCTION OF ELECTRICALLY CONDUCTIVE TITANIUM DIOXIDE POWDER

Patent number: JP4154621
Publication date: 1992-05-27
Inventor: ANDO HITOSHI; YAMAGUCHI KOICHI
Applicant: ISHIHARA SANGYO KAISHA
Classification:
- international: C01G23/04; C01G23/00; H01B1/08; C01G23/00;
H01B1/08; (IPC-1-7): C01G23/04; H01B1/08
- european:
Application number: JP19900278059 19901017
Priority number(s): JP19900278059 19901017

[Report a data error here](#)

Abstract of JP4154621

PURPOSE:To obtain TiO₂ powder having excellent electrical conductivity and whiteness by forming a coating layer of SnO₂ on the surface of a (hydrated) TiO₂ particle. **CONSTITUTION:**An aqueous suspension of TiO₂ or hydrated TiO₂ is heated at 40-90 deg.C under agitation. A solution of an Sn salt (e.g. SnCl₄) and an alkali or acid are slowly added to the above hot suspension to form a coating layer of SnO₂ hydrate on the surface of the TiO₂ particle. The amount of the coating layer is 1-30wt.% (in terms of SnO₂) based on TiO₂. The aqueous suspension is filtered and washed, the obtained cake is fractionated and recovered and, as necessary, the recovered material is dried and crushed. Finally, the product is heat-treated at 250-600 deg.C for 30min to 5hr in a non-oxidizing atmosphere (preferably in an inert atmosphere).

.....
Data supplied from the *esp@cenet* database - Worldwide